



## Technical Data Sheet ADCRYL™ AP 1062 FR

### DESCRIPTION

ADCRYL™ AP 1062 FR is a single-pack fire retardant solvent borne self-cross-linking acrylic pressure sensitive adhesive that cures at moderate temperatures upon complete solvent removal. At room temperature, full cure may take up to 24 hours.

### APPLICATION

ADCRYL™ AP 1062 FR is most suitable to produce electrical, industrial adhesive tapes and labels. It has a very good anchorage on PET, polypropylene films, paper, synthetic fabrics and foils etc.

### TYPICAL TECHNICAL SPECIFICATIONS

Test	Method	UOM	Observations
Appearance	Sight	Visual	Hazy transparent viscous liquid
Solids	Temp. 120°C (1 Hour)	%	36 ± 2
Viscosity	RVD11/Sp.No.5/10rpm at 25°C	Poise	40 to 60
Peel Adhesion	PSTC 101	gms/25mm	750 ± 10%
Shear strength (25x25mm), 1kg load	PSTC 107	Hrs	4 - 6
Rolling Ball test	PSTC 106	cm	6 - 10
Flammability test	UL 94		Passes

(\* ) Evaluated on 25 micron PET film coated with 27±2 gsm

### FEATURES

Ready to use: No need to mix	Easy to use	Fast dry	No odor	Long working time
------------------------------	-------------	----------	---------	-------------------

### INSTRUCTIONS FOR USE

ADCRYL™ AP 1062 FR should be used with proper coating equipment to the substrate. It is important that the solvents be dried efficiently in the coating machine, otherwise residual solvents could lead to a decrease in the technical characteristics of the finished product comparing to the technical specifications. Proper care should be ensured during coating process with effective ventilation.

ADCRYL™ AP 1062 FR adhesive can be mixed with different solvents such as; ketones, aromatic hydrocarbons & esters. Mix of aliphatic hydrocarbons can also be used for dilution. Solvents must be anhydrous.

*This information and any technical advice, whether verbal or written or by way of trials – are given in good faith, but without warranty; this also applies where proprietary rights of third parties are involved. The advice given does not release the user from the obligation to check its validity and to test the suitability of our products for the intended processes and uses. The application, use and processing of our products, even if made on the basis of our technical advice, are beyond our control and therefore entirely under the sole responsibility of the user.*

Date of Creation 1<sup>st</sup> January 2024



## Technical Data Sheet ADCRYL™AP 1062 FR

### PACKAGING

ADCRYL™AP 1062 FR adhesive is supplied in 200 or 225 kgs, non-returnable drums.

### STORAGE

ADCRYL AP 1062 FR is recommended to be stored in a cool place, protected from direct sunlight and heat sources, at temperatures below 35°C. Keep material in tightly closed containers to prevent loss of solvents.

Use within 6 months from production date (unopened and in the original packaging).