



Technical Data Sheet ADVANCE AP 1770

DESCRIPTION

ADVANCE AP 1770 is a high viscous, high solid content, high peel strength and high tack; solvent borne rubber-based pressure sensitive adhesive, cures at moderate temperature.

APPLICATION

ADVANCE AP 1770 is most suitable to d/s fabric tape, single side as well. It has a very good anchorage all kinds of fabric, PET, LDPE, HDPE etc.

TYPICAL TECHNICAL SPECIFICATIONS

Test	Method	UOM	Observations
Appearance	Sight	Visual	Hazy white, Viscous Liquid
Solids	Temp. 120°C (1 Hour)	%	70 ± 2%
Viscosity	RVD11/Sp.No.5/10rpm at 25°C	Poise	80 -120
Peel Adhesion	PSTC 101	gms/25mm	1700 - 2000
Tack	PSTC 106	cm	4-5

(*) Evaluated on 25-micron PET film coated with 27±2 gsm

INSTRUCTIONS FOR USE

ADVANCE AP 1770 should be used with proper coating equipment to the substrate. It is important that the solvents be dried efficiently in the coating machine, otherwise residual solvents could lead to a decrease in the technical characteristics of the finished product comparing to the technical specifications. Proper care should be ensured during coating process with effective ventilation.

ADVANCE AP 1770 adhesive can be mixed with different solvents such as; ketones, aromatic hydrocarbons & esters. Mix of aliphatic hydrocarbons can also be used for dilution. Solvents must be anhydrous.

PACKAGING

ADVANCE AP 1770 adhesive is supplied in 200 kgs, non-returnable drums.

STORAGE

ADVANCE AP 1770 is recommended to be stored in a cool place, protected from direct sunlight and heat sources, at temperatures below 35°C. Keep material in tightly closed containers to prevent loss of solvents.

SHELF-LIFE

Use within 6 months from production date (unopened and in the original packaging).

This information and any technical advice, whether verbal or written or by way of trials – are given in good faith, but without warranty; this also applies where proprietary rights of third parties are involved. The advice given does not release the user from the obligation to check its validity and to test the suitability of our products for the intended processes and uses. The application, use and processing of our products, even if made on the basis of our technical advice, are beyond our control and therefore entirely under the sole responsibility of the user.